



TYPE APPROVAL CERTIFICATE

Certificate no.:
TAK00001TH
Revision No:
1

This is to certify:

that the Glass Fibre Products

with type designation(s)

Woven Rovings: EWR270, EWR360, EWR500, EWR580, EWR600 and EWR800

issued to

Jushi Group Co., Ltd.



Job ID: 262.1-031276-2
Certificate no.: TAK00001TH
Revision No: 1

Product description

Woven Rovings: **EWR270, EWR360, EWR500, EWR580, EWR600 and EWR800.**

Legends:

E: E-Glass

WR: Woven Roving

270, 360, 500, 580, 800: Weight per unit area, g/m²

The following indicative properties have been verified by Type Testing of laminates:

Properties	Test Method	EWR270	EWR360	EWR500		
Tensile Strength – warp	ISO 527-1,4	409.04	425.57	457.28	mean	MPa
Tensile Modulus – warp	ISO 527-1,4	24.04	25.28	22.80	mean	GPa
Tensile Strength – weft	ISO 527-1,4	395.67	350.77	440.20	mean	MPa
Tensile Modulus – weft	ISO 527-1,4	23.70	23.65	24.17	mean	GPa
Fibre content by weight	ISO 1172	61.13 (0) 61.89 (90)	61.16 (0) 61.22 (90)	61.65 (0) 61.32 (90)	mean	%
Resin	TM-107					
Curing Procedure used for Type Testing	24 hrs at room temperature, 4 hrs at 80°C					

Properties	Test Method	EWR580	EWR600	EWR800		
Tensile Strength – warp	ISO 527-1,4	459.29	511.93	440.15	mean	MPa
Tensile Modulus – warp	ISO 527-1,4	24.77	26.62	23.53		

